


MAGNUM S-1000 Aggregated Texture

Architectural/Product Specifications

<p>S-1000 Aggregated Texture</p> <p>The contractor shall furnish all labor and materials required to complete the acceptable application of Magnum S-1000 in the areas specified. Upon request, the contractor shall provide sample panels coated with Magnum texture S-1000 which, when approved shall be the standards of finish to be provided.</p> <p>General Conditions</p> <p>During cold weather provide thermostatically controlled heat of 55° F minimum temperature until completely dry. Adequate ventilation should be provided at all times for proper drying. Unless otherwise indicated, Magnum Products can be used with all interior gypsum wallboards where moisture is unlikely to become a factor. Surface preparation should meet minimum Gypsum Assoc. requirements with framework meeting Hud/FHA/ALSC and local codes.</p>	<p>Magnum Aggregated Texture S-1000</p> <p>The texture finish to be used shall be Magnum Texture S-1000 as sold by Magnum Products. All material shall be delivered in original, unopened containers bearing the name of the supplier, the brand name, and the published directions for use.</p> <p>Surface Preparation</p> <p>Surfaces or patching treatments must be clean and dry. Prime metal, tie wires, etc., with rust inhibitive primer. Fill and seal wood surfaces.</p> <p>Concrete ceilings: Remove oils, grease, efflorescence or other deposits. Grind down un-level differences. Remove grinding dust and sludge.</p> <p>Gypsum wallboard ceilings: Treat joints and nail heads with any Magnum treatment products. Follow specific product directions. Smooth scratches and scuffs. All surfaces: Sharp, angular lighting accentuates plane irregularities.</p>	<p>Correct these before applying this finish. When all prepared surfaces are dry, a good quality sealer must be applied to all joints, angles, nail holes, or other porous surfaces for best results.</p> <p>Application:</p> <p>To be applied by spray only at a rate not to exceed 8 square feet per pound and in accordance with the directions printed on the container. The material is to be applied in such a fashion that it will blend in uniformly, that there is full uniform coating, and that there shall be no starved spots or other evidence of thin application. The texture shall be uniform and free of application patterns. The spray equipment shall be of such size and type as to provide acceptable results.</p> <p>Final wallboard finish should comply with the five levels of finish approved by the Gypsum Assoc., Painting and Decorating Contractors of America, and the Drywall Finishing Council.</p> <p></p> <p>P.O. BOX 15868 LENEXA, KS 66285-5868 (913) 888-0882</p>
--	--	---